

## RESIMETAL 204 Heavy Duty Ceramic Repair Paste

**Resimetal 204 Heavy Duty Ceramic Repair Paste** is a two component solvent free epoxy metal repair compound designed for heavy duty abrasion resistant repair and lining applications.

### Typical Applications

For use on equipment such as -

**chutes**

**hoppers**

**pipe bends**

**pump casings**

or any mechanical equipment and components that are subject to high abrasive wear.

### Surface Preparation

All oil and grease must be removed from the surface of the repair using an appropriate cleaner such as MEK.

For optimum performance, the surface should be abrasive blasted to **ISO 8501/4 Standard SA2.5 (SSPC SP10/ NACE 2)** and a minimum blast profile of 75 microns using an angular abrasive. Once blast cleaned, the surface must be degreased and cleaned using MEK or similar type material. All surfaces must be repaired before gingering or oxidation occurs.

PLEASE NOTE: For salt contaminated surfaces the area must be abrasive blast cleaned as mentioned above and left for 24 hours to allow any ingrained salts to come to the surface. After this 24 hour period the surface must be washed with MEK prior to brush blasting to remove the surface salts. This process must be repeated until all ingrained contaminants have been sweated out of the surface.

### Mixing and Application

***Warm the Base component to 15-25°C (60-77°F) before mixing and do not apply when the ambient or substrate temperature is below 5°C (40°F) or the relative humidity is above 90%.***

Mixing of the product can be on full units or by part-mixing. If mixing the whole unit please ensure as much of the base and activator is dispensed from the plastic container onto a clean plastic mixing surface and mix using a spatula until a uniform material free of any streakiness is achieved while ensuring no unmixed material is left on the spatula or the mixing surface. From the commencement of mixing the whole of the material should be used within 50-60 minutes at 20°C (68°F).

For part mixing, using a spatula place 3 equal measures from the base unit onto a clean plastic mixing surface. Clean the spatula thoroughly and then take one equal measure from the Activator unit and place alongside the base measures. Mix as above.

Using a spatula or applicator tool, apply the material to the blast prepared surface, ensuring the product is pressed into any holes, scars or cracks and profile the repair to a smooth finish.



## Technical data and Performance

Volume Capacity	584cc/Kg
Compressive Strength ASTM D695	1089kg/cm <sup>2</sup> (15,500psi)
Tensile Shear Adhesion ASTM D1002	148kg/cm <sup>2</sup> (2100psi)
Flexural Strength ASTM D790	420kg/cm <sup>2</sup> (6000psi)
Abrasion Resistance ASTM D4060	0.012ml per 1000 cycles – 1kg load CS17
Hardness Rockwell R ASTM D785	100
Corrosion Resistance (ASTM B117)	5000 hours

Please see Resimetal 204 Heavy Duty Ceramic Repair Paste Product Specification Sheet for further technical and performance data.

### Health and Safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read the fully detailed Material Safety Data Sheet.

**Legal Notice:** The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.